

# MATERIAL SAFETY DATA SHEET

#### SECTION 1 PRODUCT IDENTIFICATION Product Identification Polymer Lithium-Ion Rechargeable Battery Nominal PACK Capacity:2960mAh Nominal Voltage: 3.7V PACK P/N: CSP289791PA Cell P/N:PP289791AB Nominal Cell Capacity: 2960mAh Cell UL NO: Customer Model Name: PACK UL NO: Nominal PACK Capacity:2960mAh Manufacture Identification Tianjin Lishen Battery Joint-Stock CO. LTD. 86 - 22 - 83710366 Phone Number (For Information 6 Lanyuan Road, Huayuan Hi-Tech 86 - 22 - 83710366 Emergency Phone Number Telex 86 - 22 - 83710366 Industry Park, Tianjin 300384, China Http://www.lishen.com.cn Note: Blank spaces are not permitted. If any item is not applicable or no information is available, the space must be marked to indicate that. SECTION 2 HAZARDS IDENTIFICATION ■ Inhalation ■ Skin Absorption Primary Routes of Entry CARCINOGEN LISTED IN ☐ LARC Monograph All chemicals are contained in a sealed can. Risk of exposure occurs only,if the battery Health Hazards is mechanically or electrically abused (mechanical, thermal, electrical), which leads to the rupture of the battery container. Electrolyte leakage, electrode materials reaction with moisture/water or battery vent/fire may follow, depending upon the circumstances. Medical Conditions Generally Aggravated By Exposure An acute exposure will not generally aggravate any medical condition. Symptoms of Exposure Skin contact, no effect under routine handling and use. No effect under routine handling and use Eye Contact Skin Contact No effect under routine handling and use $\,$ No effect under routine handling and use Ingestion No Inhalation Reported as carcinogen Not applicable SECTION 3 COMPOSITION & INFORMATION ON INGREDIENTS Equivalent lithium content per cell COMPONENTS-Chemical Name and Common Names OSHA ACGIH OTHER LIMITS CAS Number (Hazardous Components 1% or greater, Carcinogens 0.1% or greater) PEL TLV RECOMMENDED Lithium Cobaltite 41% 12190-79-3 Graphite Carbon 21% 7782-42-5 Lithium Hexafluorophosphate 4% 21324-40-3 Organic solvent 14% Non-Hazardous Ingredients(tabs,pouch,separator,etc.) 20% 100% Total SECTION 4 FIRST-AID MEASURES If exposure to internal materials in cell due to damaged outer casing, the following actions are recommended. Eve Contact In case of eye contact, flush with lot of water for 15 minutes, and get medical help. In case of skin contact with contents of battery, flush immediately with water. Skin Contact In case of light inhalation ,move to an area with flash air immediately, if irritation persists, get medical help. In case of ingestion, drink milk/water to induce vomitting and wash out,get medical Ingestion SECTION 5 FIREFIGHTING MEASURES Extinguisher Media:

## Special Fire-Fighting Procedures:

CO2 or dry chemical power

In case of fire in cell original containers, use CO2 or dry chemical extinguisher; For fire in an djacent area, water can be used.

## SECTION 6 ACCIDENTAL RELEASE MEASURES

On Land:

Place material into suitable containers, If the skin has come into contact with the electrolyte, it should be washed thoroughly with water, Sand or earth should be used to absorb any exuded material. Seal leaking battery and contaminated absorbent material should be treated by local regulation, and call local fire/police department to ask for help.

In Water:

If possible, remove from water far from body in special fixture, and call local fire/police department to ask for help



## SECTION 7 HANDING AND STORAGE

lling: Take all precautions mentioned in this document and operate the pattery within the temperature range or -20°C and 45°C.

No special protective clothing required for handling individual cells in corrective operational method. Improper handling of lithium ion battery may result in injury or damage from electrolyte leakage, heating, ignition or explosion. So do not crush, pierce, short cell/battery terminals with conductive material; Do not directly heat or solder; do not throw into fire; do not place cell/battery in non conductive travs

#### Storage:

Store the battery in a cool, drying place, without chemical vapor or excessive humidity.

#### SECTION 8 EXPOSURE CONTROLS & PERSONAL PROTECTION

#### Engineering Controls:

keep away from heat and open flame, prevent hard & sharp thing penetration, store in a cool & dry

#### Personal Protection:

Respiratory Protection: Not necessary under normal operations condition. SCBA required in the event of a fire

Eye/Face Protection: Not necessary under normal operation condition. Glove protection: Not necessary under normal operation condition.

Foot Protection: Steel toed shoes recommended for Large container handling.

	□ Local Exhaust	□ Mechanical (General)
Ventilation to Be Used	Not necessary under conditions of Normal use.	Not necessary under conditions of Normal use.
		□ Special
		Not necessary under conditions of Normal use.
	□ Other (Specify)	

Not necessary under normal operation conditions.

#### Other Protective Clothing and Equipment

Not necessary under normal operation conditions

## Hygienic Work Practices

Not necessary under normal operation conditions

## SECTION 9 PHYSICAL /CHEMICAL PROPERTIES

#### Specific Gravity (H2O=1):

LiCoO<sub>2</sub>:3.80 Graphite:2.0~2.2

#### Melting Point:

Graphite:3500-3900℃ LiCoO2:1130°C

## Appearance and Odor:

 ${\tt LiCoO_2}$  is a gray odorless power; Graphite is a black or odorless power;

Organic solvent is a colorless liquid; Lithium salt is a white, crystalline and odorless power.

## SECTION 10 STABILITY & REACTIVITY DATA

tability Conditions to Avoid:				
■ Stable	Do not heat or incinerate the battery, Never impact, pierce or crush the battery.			
□ Unstable	Do not disassemble or modify the battery,			
	Do not charge the battery under high temperature conditions such as near a fire or the direct sunlight.			
	Do not shot-circuit the battery by connect the positive and negative terminals with a metal material.			
	Do not allow the battery to get wet or be immersed in water.			

## Incompatibility (Materials to Avoid)

Water, salted water, other solvent with water

## Hazardous Decomposition Products

## Hazardous Polymerization

□ May Occur

Conditions to Avoid

## SECTION 11 TOXICOLOGICAL INFORMATION

This product does not elicit toxicological properties during routine handling and use.

# SECTION 12 ECOLOGICAL INFORMATION

Cobalt and its compounds can pose a threat if released to environment. The detail information are showed in waste disposal method in Section 13 "Disposal Consideration".



## SECTION 13 DISPOSAL CONSIDERATIONS

There is no contamination during normal operation and use. Lithium batteries should have their terminals insulated prior to disposal, do not throw away a used battery and provide them for recycling company.

Open cells should be treated as hazardous waste. If the leakage or other material is Released, we should take actions as follows:

Leave the area, allow the batteries to cool down, let the vapors to dissipate .

Avoid skin and eye contact or inhalation of vapors. Remove spiller liquid with absorbent and incinerate

## Waste Disposal method Opened cells should be treated as hazardous waste.

Incineration: incineration should never be performed by battery users but eventually by trained professionals in authorized facilities with proper gas and fumes treatment.

Landfilling:According to the proper laws and regulations in different countries or areas, the battery should be buried deeply in the specified place;

Recycling: Send to authorized recycling facilities to get Co,Cu and Al, eventually through licensed

## SECTION 14 Transportation

Lishen's DAP574868PA Lithium-Ion Polymer batteries are considered to be "Rechargeable Lithium Ion Polymer Batteries" and meet the requirements of transportation by the United States Department of Transportation (DOT), International Civil Aviation Administratration (ICAO), International Air Transportation Association (IATA) special provision UN3480 as "non-dangerous goods" or "non-hazardous materials". These lithium batteries can be transported in nonrestrictive material and as Non-Dangerous Goods as they meet all the requirements in below:

1	Lithium content requirement
1.1	For the bar cells, the lithium content can not overpass 20Wt/h;
1.2	For the batteries, the lithium content can not overpass 100Wt/h;
2	Meet with UN Test Requirement
	All the cell and battery must be verified to meet with all the requirements in Part $3$ -38.3 item (UN38.3 tests) for "Recommendations on the Transport of Dangerous Goods, Manual of Tests and Criteria" .
3	Package Requirement
1.1	The cell and battery must be packaged specially and singly, and put into hard outer package to prevent short-circuit if they do not be assembled in finished equipments (such as mobile phone,camera,NBPC.and so on)
1.2	The cell quantity is more than 24pcs or the battery quantity is more than 12pcs, they must be asked to meet with the requirements in blow besides they are assembled in finished equipment.
a	Every package must be marked in the content that the packages are loaded in lithium cells or batteries, also add new lithium iron opertion label , also need point out the corrective actions when the packages are damaged.
b	Every batch shipment must be appendixed document which should contain the content that the packages are loaded in lithium cells or batteries, also need point out the corrective actions when the packages are damaged.
c	Every package must pass 1.2mm fall test in any direction. No damage for the cells and batteries, no move and touch together, no cells or batteries escape from the package.
	Every package weight can not overpass 10kg if the batteries can not be assembled in finished

## SECTION 15 REGULATORY INFORMATION

0201101110	ILLOCE III OILI III	O.C. MILITOIN
OSHA Hazard Com	munication Standard ( 29 CFR 19	)10.1200)
	Hazardous	✓ Non-hazardous

# SECTION 16 OTHER INFORMATION

equipment.

There is no hazards in accordance with the UN recommendations test.(UN manual of tested and criteria 38.3)

Pack Part Number	CHP289791PA
Nominal Voltage	3.7V
Nominal Pack Capacity	2960mAh
Pack Mass	56g
Equivalent Lithium Content	0.888g

Test NO	Test Item	Criteria	Result	Remark
38. 3. 4. 1	Altitude Test	No mass loss,leakage,venting,disassembly,rupture,and fire.OCV should not be less than 90% before testing	Passed	
38. 3. 4. 2	Thermal Test	No mass loss,leakage,venting,disassembly,rupture,and fire.OCV should not be less than 90% before testing	Passed	
38. 3. 4. 3	Vibration	No mass loss,leakage,venting,disassembly,rupture,and fire.OCV should not be less than 90% before testing	Passed	
38. 3. 4. 4	Shock	No mass loss,leakage,venting,disassembly,rupture,and fire.OCV should not be less than 90% before testing	Passed	
38. 3. 4. 5	External Short Circuit	External temperature should not exceed 170degC. No disassembly, and fire within six hours of this test.	Passed	
38. 3. 4. 6	Impact	External temperature should not exceed 170degC. No disassembly, and fire within six hours of this test.	Passed	
38. 3. 4. 7	Overcharge	No disassembly, and fire within seven days of this test.		Only for battery
38. 3. 4. 8	Forced Discharge	No disassembly, and fire within seven days of this test.	Passed	